



Final Report on

ONR Grant No. N00014-02-1-0984

NANOSTRUCTURES FOR ENHANCED ELECTRON/HOLE CONVERSION

Principal Investigators:

Arthur C. Gossard and Herbert Kroemer

Materials Department, University of California

Santa Barbara, CA 93106-5050

gossard@engineering.ucsb.edu; kroemer@ece.ucsb.edu

Submitted to:



Office of Naval Research

Attention: Dr. Colin H. Wood

875 N. Randolph Street, Suite 1425

Arlington, VA 22203-1995

March 13, 2009

20090319159

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to the Department of Defense, Executive Service Directorate (0704-0188). Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ORGANIZATION.					
1. REPORT DATE (DD-MM-YYYY) 3/13/2009		2. REPORT TYPE Final Technical Report		3. DATES COVERED (From - To) 10/1/02 - 9/30/06	
4. TITLE AND SUBTITLE Nanostructures for Enhanced Electron/Hole Conversion			5a. CONTRACT NUMBER		
			5b. GRANT NUMBER N00014-02-1-0984		
			5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S) Arthur C. Gossard and Herbert Kroemer			5d. PROJECT NUMBER		
			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER 312		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) The Regents of the University of California Office of Research 3227 Cheadle Hall, 3rd Floor Santa Barbara, CA 93106-2050				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research 140 Sylvester Road Building 140, Room 218 San Diego, CA 92106-3521				10. SPONSOR/MONITOR'S ACRONYM(S) ONR	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT "Approved for Release; Distribution is Unlimited."					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT In this program we used molecular beam epitaxy (MBE) to create epitaxial metal-semiconductor structures containing embedded metallic nanoparticles, metallic epitaxial films and epitaxial metal-semiconductor junctions. We incorporated epitaxial metallic nanoparticles of erbium arsenide and erbium antimonide in GaAs, InGaAs and GaSb structures by molecular beam epitaxy. The metallic nanoparticles in semiconductors produced: 1) electrical doping of semiconductors, 2) electron/hole recombination enhancement, 3) electron/hole tunnel junction enhancement, 4) thermal conductivity control, 5) microwave rectification improvement and 6) strong electron plasma resonances. Tunnel currents of GaAs np junctions were enhanced by up to five orders of magnitude by the embedded nanoparticles. Electron-hole recombination times in a series of ErAs/InGaAs codepositions were reduced to less than 100 femtoseconds. We produced the first epitaxial growth of GdN on GaN. This research thus established a foundation for development of improved artificially structured thermoelectric power generation materials, for new materials for Terahertz wave generation and detection and for development of highly conducting contacts for the nitride semiconductors.					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES 7	19a. NAME OF RESPONSIBLE PERSON Arthur C. Gossard
a. REPORT	b. ABSTRACT	c. THIS PAGE			19b. TELEPHONE NUMBER (include area code) 805.893.2686

Final Technical Report:

Nanostructures for Enhanced Electron/Hole Conversion

A. C. Gossard and H. Kroemer, University of California Santa Barbara

Office of Naval Research Grant No. N00014-02-1-0984

Final Report for 07/31/2003 to 07/31/2006:

In this program we created, studied, and developed applications for epitaxial metal-semiconductor heterostructures and nanostructures. The epitaxial metal-semiconductor nanocomposites are new electronic materials that can have substantially different properties from conventional doped semiconductors. Our approach was to use molecular beam epitaxy (MBE) growth to create epitaxial metal-semiconductor structures containing embedded nanoparticles, epitaxial films and metal-semiconductor junctions. Unlike current electronic technologies that must rely on individual dopant atoms to provide carriers and on highly imperfect polycrystalline metal films to provide electrical contacts, the new epitaxial nanoparticles and films provide a wide distribution of electron energies within a semiconductor and provide a very controlled and perfect contact to semiconductors. We studied these materials with the goal of reduction and engineering of semiconductor p-n junction barriers by embedding metallic nanoparticles in the junctions. We incorporated epitaxial metallic nanoparticles of erbium arsenide and erbium antimonide in GaAs, InGaAs and GaSb structures by molecular beam epitaxy growth. Collaborating faculty member Susanne Stemmer obtained direct evidence from Z-contrast scanning transmission electron microscopy that the metal nanoparticles of ErAs grow in a perfectly registered rocksalt structure within the zincblende semiconductor host. Current-voltage measurements showed that

1) Tunnel currents of GaAs np junctions were enhanced by up to five orders of magnitude at room temperature at one volt forward bias by incorporation of 1.2 monolayers of ErAs deposition at the junction between the n ($5 \times 10^{18} \text{ cm}^{-3}$) and p ($2 \times 10^{19} \text{ cm}^{-3}$) GaAs. The tunnel currents exceeded 10^5 A/cm^2 at +1 V forward bias.

- 2) The tunnel current enhancement was approximately one order of magnitude greater at +1 V bias for ErAs-enhanced GaAs junctions for p grown on n compared to n grown on p.
- 3) The tunnel current enhancement was approximately one order of magnitude greater at +1 V bias for ErAs-enhanced GaAs junctions relative to $\text{Al}_{1.1}\text{Ga}_{0.9}\text{As}$ junctions.
- 4) The tunnel current enhancement was approximately one order of magnitude greater at +1 V bias for $p = 2 \times 10^{19} \text{ cm}^{-3}$ doping of GaAs junctions compared to $p = 4 \times 10^{18} \text{ cm}^{-3}$ doping.
- 5) The tunnel current enhancement was approximately one order of magnitude greater at +1 V bias for 1.2 monolayers of ErAs deposition compared to 0.2 monolayers of ErAs deposition.
- 6) The form of the tunneling current versus voltage characteristic in the enhanced junctions was well represented by a model of tunneling in series through back to back metal- semiconductor junctions.

The first metal-semiconductor junctions (of TiPtAu on n-doped GaAs ($n = 1 \times 10^{17} \text{ cm}^{-3}$)) with and without a 0.6 monolayer deposition of ErAs two nanometers below the metal-semiconductor interface were also grown and studied. The structure with ErAs had a reduced Schottky barrier and a more ideal tunnel characteristic compared to structures with no enhancing ErAs deposition.

Carrier concentrations and electron-hole recombination rates were measured in a series of ErAs/InGaAs superlattices. Samples with 40 nm periods showed a decrease in conduction electron concentration as the deposition of ErAs increased from 0.4 to 1.6 monolayers. Samples with depositions of 1.2 and 1.6 monolayers froze out at low temperature, while samples with depositions of 0.4 and 0.8 monolayers remained fully metallic with $\sim 10^{12}$ electrons per cm^2 per layer of ErAs. Partial compensation of the carriers was achieved by modulation doping the regions near the ErAs layers with beryllium acceptors. Reduction of the superlattice period from 40 nm to 5 nm reduced electron-hole recombination times to ~ 2 ps (at 40 nm period) and ~ 0.05 ps (at 5 nm period).

In cooperation with Professor Elliott Brown, Gossard's students grew and characterized epitaxial Schottky diodes of epitaxial ErAs films on InGaAlAs of various Al contents. Reducing the Al content in the InGaAlAs reduced the Schottky barrier height continuously down to and including zero eV.

Diodes with optimum responsivity at zero applied bias were produced and measured.

We also grew fully epitaxial diodes of n-doped InAs on p-doped GaSb. Forward currents of >1000 Amps per cm^2 were measured at +1 Volt bias and were limited primarily by Ohmic contact resistance.

The metallic nanoparticles in semiconductors produced: 1) electrical doping of semiconductors, 2) electron/hole recombination enhancement, 3) electron/hole tunnel junction enhancement, 4) thermal conductivity control, 5) microwave rectification improvement and 6) strong electron plasma resonances.

ErAs particles in GaAs p-n tunnel junctions allowed much stronger tunneling than conventional p-n junctions. p-ErAs-n junctions showed up to 10^5 times more current than comparable p-n junction at 1 Volt forward bias. We synthesized cascaded photovoltaics with ErAs enhanced tunnel junctions that produced CW radiation up to 2 THz.

We also formed epitaxial thin films of ErAs on GaAs and InGaAlAs for highly ideal and engineerable low-defect contacts and barriers for sensitive low noise mm-wave and THz detection. We measured NEP of $<9 \times 10^{-13} \text{ W Hz}^{-1/2}$ giving -63 dBm sensitivity at 3.1 GHz with a 8kHz bandwidth.

We developed epitaxial metal-semiconductor heterostructures and nanostructures with record-breaking performance in several areas.

1. **Cascaded solar cells with increased efficiency.** Grew cascaded AlGaAs solar cells with ErAs-enhanced tunnel junctions with output voltages of 2.1 Volts (versus 1.2 Volts with conventional tunnel junctions).
2. **ErAs nanoparticle arrays.** Produced high densities of metal nanoparticles in InGaAs by co-deposition of ErAs and semiconductor species. The arrays have high electrical conductivity, low thermal conductivity and are promising for thermoelectric power generation
3. **Highly conductive epitaxial Ohmic contacts.** Produced epitaxial ErAs epitaxial films on graded InGaAs structures. Contact resistances are less than 2 Ohm-micron^2 .
4. **Low noise epitaxial Schottky microwave detectors.** Produced epitaxial ErAs/InAlGaAs detectors with noise equivalent power below $10^{-11} \text{ W/Hz}^{1/2}$ at 640 GHz.

5. **Terahertz detectors.** Produced ErAs nanoparticles in GaAs with best reported bandwidth and efficiency for Terahertz detectors (10 times better than radiation-damaged SOS detectors and LT-GaAs detectors).

6. **GdN on gallium nitride:** We produced the first epitaxial growth of GdN on GaN. We found growth conditions to produce micron-thick epitaxial films of GdN on GaN templates. We produced GdN (111) films with rocksalt structure on (0001) GaN at substrate temperatures below $T = 500\text{C}$.

The research accomplished under this grant thus established a foundation for development of highly conducting contacts for the nitride semiconductors, for development of improved artificially structured thermoelectric power generation materials, and for new materials for Terahertz wave generation and detection.

Publications:

Driscoll DC, Hanson MP, Mueller E, **Gossard AC. Growth and microstructure of semimetallic ErAs particles embedded in an InGaAs matrix.** *Journal of Crystal Growth*, vol.251, no.1-4, April 2003, pp.243-7

Sukhotin M, Brown ER, Driscoll D, Hanson M, **Gossard AC. Picosecond photocarrier-lifetime in ErAs:InGaAs at 1.55 microns.** *Applied Physics Letters*, vol.83, no.19, 10 Nov. 2003, pp.3921-3

Pohl P, Renner FH, Eckardt M, Schwanhausser A, Friedrich A, Yuksekdag O, Malzer S, Dohler GH, Kiesel P, Driscoll D, Hanson M, **Gossard AC. Enhanced recombination tunneling in GaAs pn junctions containing low-temperature-grown-GaAs and ErAs layers.** *Applied Physics Letters*, vol.83, no.19, 10 Nov. 2003, pp.4035-7.

Hanson MP, Driscoll DC, Kadow C, **Gossard AC. Metal/semiconductor superlattices containing semimetallic ErSb nanoparticles in GaSb.** [Journal Paper] *Applied Physics Letters*, vol.84, no.2, 12 Jan. 2004, pp.221-3

Hanson MP, Driscoll DC, Zimmerman J, Brown ER, **Gossard AC. Subpicosecond photocarrier lifetimes in GaSb/ErSb nanoparticle superlattices at 1.55 micron.** *Applied Physics Letters*, vol. 85, no. 15 (Oct. 11, 2004), pp. 3110-3112

Bjarnason JE, Chan TLJ, Lee AWM, Brown ER, Driscoll DC, Hanson M, **Gossard AC, Muller RE. ErAs:GaAs photomixer with two-decade tunability and 12 microwatt peak output power.** *Applied Physics Letters*, vol.85, no.18, 1 Nov. 2004, pp.3983-5.

Hanson MP, Driscoll DC, Zimmerman JD, **Gossard AC, Brown ER. Subpicosecond photocarrier lifetimes in GaSb/ErSb nanoparticle superlattices at 1.55 microns.** *Applied Physics Letters*, vol.85, no.15, 11 Oct. 2004, pp.3110-12.

Dorn A, Peter M, Kicin S, Ihn T, Ensslin K, Driscoll D, **Gossard AC. Charging effects of ErAs islands embedded in AlGaAs heterostructures.** *Elsevier. Physica E - Low-Dimensional Systems & Nanostructures*, vol.21, no.2-4, March 2004, pp.426-9.

Driscoll DC, Hanson MP, **Gossard AC. Carrier compensation in semiconductors with buried metallic nanoparticles.** *Applied Physics Letters*, vol. 97, no. 1, January 1, 2005, p. 016012

Driscoll DC, Hanson MP, **Gossard AC, Brown ER. Ultrafast photoresponse at 1.55 μm in InGaAs with embedded semimetallic ErAs nanoparticles.** *Applied Physics Letters*, vol. 86, no. 5 (January 31, 2005) p. 051908

G H Döhler, F Renner, O Klar, M Eckardt, A Schwanhäuß, S Malzer, D Driscoll, M Hanson, A. C. Gossard, G Loata, T Löffler and H Roskos. **THz-photomixer based on quasi-ballistic transport.** *Semiconductor Science and Technology*, vol. 20, July, 2005, pp. S178-S190.

Klenov DO, Zide JM, Zimmerman JD, **Gossard AC, Stemmer S. Interface atomic structure of epitaxial ErAs layers on (001) InGaAs and GaAs.** *Applied Physics Letters*, vol.86, no.24, 13 June 2005, pp.241901-1-3

Prasankumar RP, Scopatz A, Hilton DJ, Taylor AJ, Averitt RD, Zide JM, **Gossard AC. Carrier dynamics in self-assembled ErAs nanoislands embedded in GaAs measured by optical-pump terahertz-probe spectroscopy.** *Applied Physics Letters*, vol.86, no.20, 16 May 2005, pp.201107-1-3.

Russell KJ, Appelbaum I, Narayanamurti V, Hanson MP, **Gossard AC. Transverse momentum nonconservation at the ErAs/GaAs interface.** [Journal Paper] *Physical Review B-Condensed Matter*, vol.71, no.12, 15 March 2005, pp.121311-1-4

Klenov DO, Driscoll DC, **Gossard AC, Stemmer S. Scanning transmission electron microscopy of ErAs nanoparticles embedded in epitaxial In/sub 0.53/Ga/sub 0.47/As layers.** *Applied Physics Letters*, vol.86, no.11, 14 March 2005, pp.111912-1-3.

Driscoll DC, Hanson MP, **Gossard AC, Brown ER. Ultrafast photoresponse at 1.55 μm in InGaAs with embedded semimetallic ErAs nanoparticles.** *Applied Physics Letters*, vol.86, no.5, 31 Jan. 2005, pp.51908-1-3.

Driscoll DC, Hanson MP, **Gossard AC. Carrier compensation in semiconductors with buried metallic nanoparticles.** *Journal of Applied Physics*, vol.97, no.1, 1 Jan. 2005, pp.16102-1-3.

Trumm S, Betz M, Sotier F, Leitenstorfer A, Schwanhauser A, Eckardt M, Schmidt O, Malzer S, Dohler GH, Hanson M, Driscoll D, Gossard AC.
Ultrafast spectroscopy of impact ionization and avalanche multiplication in GaAs. *Applied Physics Letters*, vol. 88, no. 13 (March 27, 2006) p. 132113.

Hanson, MP, Gossard, AC, Brown, ER. **ErAs as a transparent contact at 1.55 microns.** *Applied Physics Letters*, vol. 89, no. 11 (Sept. 11, 2006), p. 111908